

Power-Lift Grease PL-10™

Absolutely one of the best anti-wear, extreme-pressure, lithium complex greases designed to meet the highest requirements for film strength, operating temperatures and lubrication life – essential for the reliable operation of today's equipment

Key Features & Benefits

- Provides extreme-pressure protection under all lubrication conditions
- Lowers operating temperatures
- Protects from friction-related heat and wear
- Protects against rust and corrosion
- Extends equipment life
- Reduces maintenance, downtime and related expenses
- Excellent water washout and spray off resistance
- Continuous operating range: 0°F to 450°F (-17°C to 232°C)
- Typical dropping point: 525°F+ (273°C+)
- NLGI #2
- Treats, seals and protects metal surfaces for reduced friction and wear
- Contains **Muscle Metal Treatment MT-10®** technology for increased lubricity and boundary film lubrication

Typical Applications

- Bearings
- Automotive wheel bearings
- Universal joints
- CV joints
- Chassis fittings
- Axles
- Conveyors
- Pumps
- Firearms
- Fishing reels and tackle
- Sports equipment
- Other industrial, automotive or commercial areas of lubrication requiring an extreme-pressure, anti-wear grease

Technical Data

| | |
|--|--------------------------------|
| Appearance..... | Cream, smooth/tacky semi-solid |
| Odor..... | Bland |
| NLGI grade | 2 |
| Thickener type..... | Lithium |
| Soap type | Lithium complex |
| Antirust corrosion inhibitor..... | Yes |
| Corrosion test..... | Pass |
| Base oil viscosity @ 40°C, SUS..... | 775 - 825 |
| Cone penetration @ 77°F, 60 strokes..... | 265-295 |
| 100,000 strokes | +10% |
| Dropping point..... | > 525°F (> 273°C) |
| Pour point..... | 0°F (-17.8°C) |
| Density @ 20°C, g/cm³ | 1.0216 |
| Lbs per gal (U.S.) | ~ 8.525 |
| Flash point | > 437°F (> 225°C) |
| Fire point..... | 580°F (304°C) |
| Roll stability..... | +/- 6 |
| Oxidation PSI @ 100 hr., 500 hr | 5, 10 |
| Timken OK Load, lbs..... | 60 |
| Shear stability..... | < 10% |
| Wheel bearing, % loss | 0 - 1 |
| Four-ball weld point, kg..... | 1000 |
| Four-ball wear, mm | 0.56 |
| Water resistant..... | Yes |
| Water washout @ 170°F | 3 - 8 |
| Mobility, g/min 0°C, 20°C | 3, 35 |
| Solubility | Negligible (water) |

The above properties are typical values and do not constitute a product specification.

Container Availability

| | |
|---------------------|--------------------------|
| Item PL-10-T | 1 oz. jar (28 g) |
| Item PL-10-C..... | 14 oz. cartridge (396 g) |
| Item PL-10-LB..... | 16 oz. jar (453 g) |
| Item PL-10-5LB..... | 72 oz. tub (2 kg) |
| Item PL-10-P..... | 35 lb pail (15.8 kg) |
| Item PL-10-K..... | 120 lb drum (54.4 kg) |
| Item PL-10-D..... | 400 lb drum (181.4 kg) |

Transportable tank and other bulk container availability upon request. Other NLGI grades may be available upon request.